

Technical Data Sheet

COATED PVC TARPAULIN

Item	G018	G019	G020	G021
Weight (g/m ²) *	610± 20	650± 20	700± 20	950± 20
Breaking Strength (N/5cm) *	2300/2100	2250/2600	2250/2600	2250/2600
Tearing Strength (N) *	350/300	370/320	370/320	370/320
Adhesion (N/5cm) *	80	80	80	80
Width	up to 350cm			
FR Certification	M2, B1, B2, DIN75200, NFPA 701			
Lacquering	Acrylic or PVDF			
Cd%, Pb%, As%, Ba%, Cr%, Hg%, Se%	EN71-3			
Features	High intensity, good elasticity coated PVC tarpaulin used for truck cover, tent, awning, and covers, etc.			

* Test method: DIN53352 BS3424

LAMINATED PVC TARPAULIN

Item	G027	G028
Weight (g/m ²) *	610± 20	650± 10
Breaking Strength (N/5cm) *	1450/1350	1450/1350
Tearing Strength (N) *	300/250	300/250
Adhesion (N/5cm) *	70	70
Width	up to 350cm	
FR Certification	M2, B1, B2, DIN75200, NFPA 701	
Lacquering	Acrylic or PVDF	
Cd%, Pb%, As%, Ba%, Cr%, Hg%, Se%	EN71-3	
Features	Laminated pvc tarpaulin used for tent, awning, and covers, etc.	

* Test method: DIN53352 BS3424

