



**Polyethylene Banner Printing Media**

Item	140JP05	TEST METHOD
Weight	140g/m <sup>2</sup> ± 5%	BS 2471
Thickness	0.20mm ± 0.02	BS 2544
Base Fabric	1000 x 1000 dtex	---
Tensile Strength	34.34kg / 27.64kg	ASTMD751-95
Tearing Strength	20kg/18kg	ASTMD4533-91
Width	up to 320cm	
FR Certification	We can reach B1, NFPA701	

**Applications**

	Banner	Billboard	Building Wrap	Display Systems
Applications	■	■		■

■-Excellent □-Good



**Ink Printability**

Solvent	Eco Solvent	UV	Screen Printing
■	■	■	

The values of physical and chemical are intended only as a resource of information. They are given without guaranty and do not constitute a warranty.



**Polyethylene Banner Printing Media**

Item	180JP06/07	TEST METHOD
Weight	180g/m <sup>2</sup> ± 5%	BS 2471
Thickness	0.20mm ± 0.02	BS 2544
Base Fabric	1000 x 1000 dtex	--
Tensile Strength	40.97kg / 31.25kg	ASTMD751-95
Tearing Strength	34kg/38kg	ASTMD4533-91
Width	up to 320cm	
FR Certification	We can reach B1, NFPA701	

**Applications**

	Banner	Billboard	Building Wrap	Display Systems
Applications	■	■		■

■-Excellent □-Good



**Ink Printability**

Solvent	Eco Solvent	UV	Screen Printing
■	■	■	

The values of physical and chemical are intended only as a resource of information. They are given without guaranty and do not consititue a warranty.